

Product Specification Sheet

Telefon: +49 (0) 9721 79398-0
Telefax: +49 (0) 9721 79398-14
E-Mail: info@labelident.de
Internet: www.labelident.com

EL-AA / EB-AA

**Removable, matte white polyester labels
on sheet for full-color copying machines and laser printers**

Material Thickness:

| | Value (Tolerance) | Unit | Norms |
|------------------|-------------------|--------|---------|
| Facestock | 50 (+/- 10%) | micron | |
| Adhesive | 18 -20 (+/- 3) | micron | |
| Liner (glassine) | 101 (+/- 6%) | micron | ISO 534 |

Adhesive (acrylic):

| | | Value | Unit | Test Method |
|------------------------------|----------------------|----------|-------|----------------|
| Shear Strength | | 20 | hours | FTM 8 on steel |
| Initial Tack | | 4 | N | FTM 9 on glass |
| Tackiness | Contact time 0 min. | 2,5/25 | N/m | FTM 1 on glass |
| | Contact time 20 min. | 3,0/25 | N/m | FTM 1 on glass |
| | Contact time 24 h | 3,5/25 | N/m | FTM 1 on glass |
| Application Temperature | | min. +5 | °C | |
| Temperature Range (Adhesive) | | 0 to +80 | °C | |

*no information provided by the manufacturer

Certifications: Adhesive is approved by ISEGA (Direct contact dry & moist, non fatty foodstuffs), adhesive is solvent free.

Printability: Specially designed laser printable material (black and white and coloured) for product, logistics and industrial variable information applications

Storage: Material is stable for two years stored at max. 21°C and 50% rel. humidity. Damp conditions, excessive heat and/or cold conditions should be avoided.

Further Information: Application environments and certain surfaces such as vinyl, glass, acrylic, styrene, polycarbonate may cause increased adhesion and adhesive transfer. Applied to polyester application surfaces, adhesive shows increased peel and has the tendency to become permanent. We recommend that all surfaces be tested for compatibility and removability.

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: January 2019.

Labelident GmbH
Parisstraße 5
D-97424 Schweinfurt

Commerzbank Schweinfurt
SWIFT-BIC: COBADEFFXXX
IBAN: DE76 7934 0054 0655 2228 00

Amtsgericht Schweinfurt: HRB 4597
Geschäftsführung: Thomas Simon, Frithjof von Kessel
Steuernummer: 13/203/03339
Ust.-ID: DE814048229