

Product Specification Sheet

ERT-AA

Printable with resin ribbon (FTA-LH...x...) for foil labels

**Removable, top-coated glossy white polyester labels
on roll for thermal transfer printers**

Material Thickness:

	Value (Tolerance)	Unit	Test Method
Facestock	50 (+/- 10%)	micron	ASTM D 3652
Adhesive	23-25 (+/- 3)	micron	ASTM D 3652
Liner (glassine)	56 (+/- 10%)	micron	ASTM D 3652

Adhesive (acrylic):

		Value	Unit	Test Method
Expected Shear		100	hours	FTM 8
Tack		200,0	gm/cm ²	ASTM D 2979
Adhesion from (average)	Stainless Steel	32	N/m	FTM 1 (modified for 72 hr dwell time)
	Glass	*		
	Polypropylene	*		
	Paint (automotive)	*		
	PBT	*		
Application Temperature		min. +10	°C	
Temperature Range (Adhesive)		-29 to +150	°C	

*no information provided by the manufacturer

Certifications: Material meets REACH and RoHS requirements (2011/65/EU). IMDS data available.

Printability: Suited for thermal transfer printing with resin ribbons (i.e. Armor AXR® 7+, AXR® 8; Labelident resin, Labelident Ultra resin; Zebra 4800, 5095, 5100, Coding TTR).

Storage: Material is stable for two years stored at max. 21°C and 50% rel. humidity. Damp conditions, excessive heat and/or cold conditions should be avoided.

Further Information: Application environments and certain surfaces such as vinyl, glass, acrylic, styrene, polycarbonate may cause increased adhesion and adhesive transfer. Applied to polyester application surfaces, adhesive shows increased peel and has the tendency to become permanent. We recommend that all surfaces be tested for compatibility and removability.

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: January 2019.