

Product Specification Sheet

ERT-PABE / ERT-PAGN / ERT-PARD / ERT-PAYW

Printable with wax ribbon (FTA-LW...x...) for paper labels

Telefon: +49 (0)9721 47699-0

Telefax: +49 (0)9721 47699-14

E-Mail: info@labelident.de

Internet: www.labelident.com

**Removable, matte colored paper labels
on roll for thermal transfer printers**

Material Thickness:

	Value (Tolerance)	Unit	Test Method
Facestock	82 (75-90)	micron	ISO 534
Adhesive	15	micron	
Liner (glassine)	52 (50-58)	micron	ISO 534

Adhesive (acrylic):

		Value	Unit	Test Method
Shear Strength		100	min	FTM 8
Initial Tack		10,3	N	FTM 9
Peel Resistance	Stainless Steel	15,4	N/25 mm	FTM 1 (72 hours)
	Glass	*		
	Polypropylene	*		
	Paint (automotive)	*		
	PBT	*		
Application Temperature		min. +5	°C	
Temperature Range (Adhesive)		-20 to +80	°C	

*no information provided by the manufacturer

Certifications: Facestock: Packaging and packaging waste Directive 94/62/CE, Electric and electronic equipment (RoHS) Directive 2011/65/EU; Adhesive: Packaging and packaging waste Directive 94/62/CE, EN 71-3 Toy Safety, EN 71-9 Toy Safety, Liner: Contact with foodstuff (BfR XXXVI), Packaging and packaging waste Directive 94/62/CE, EN 71-3 Toy Safety, Electric and electronic equipment (RoHS) Directive 2011/65/EU. Paper from sustainable forestry (FSC certified).

Printability: Suited for thermal transfer printing with wax ribbons (i.e. Armor AWR®8, AWR®470, AWX®FH; Labelident Eco wax; Zebra 2100, 2300) or combination ribbons (i.e. Armor APR®6, APX®FH; Kurz K200, K305; Zebra 3200, 3400).

Storage: Material is stable for two years stored at max. 21°C and 50% rel. humidity. Damp conditions, excessive heat and/or cold conditions should be avoided.

Further Information: n/a

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: August 2018.