

Product Specification Sheet

GOB-WE / GOB-YW / KFL_._WE / KFL_._YW

**Permanent, matte white or yellow coated nylon labels
 on sheet for full-color copying machines and laser printers**

Material Thickness:

	Value (Tolerance)	Unit	Test Method
Facestock	143	micron	ASTM D 3652
Adhesive	15	micron	ASTM D 3652
Liner (glassine)	64 +/- 4	micron	ASTM D 3652

Adhesive (acrylic):

		Value	Unit	Test Method
Shear Strength		3	hours	
Initial Tack		*		
Peel Resistance	Stainless Steel	13	N/25 mm	FTM 1 (24 hours)
	Glass	*		
	Polypropylene	*		
	Paint (automotive)	*		
	PBT	*		
Application Temperature		min. 0	°C	
Temperature Range (Adhesive)		0 to +80	°C	

*no information provided by the manufacturer

Certifications: Material meets REACH and RoHS requirements (2011/65/EU). Material is free of plastizisers, free of silicones (except liner) and halogens.

Printability: Suited for full-color copying machines and laser printers.

Storage: Material is stable for two years stored at max. 21°C and 50% rel. humidity. Damp conditions, excessive heat and/or cold conditions should be avoided.

Further Information: Not suitable for washing processes.

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: January 2019.