

## Product Specification Sheet

### FTA-LW

Telefon: +49 (0)9721 47699-0  
Telefax: +49 (0)9721 47699-14

### Labelident wax thermal-transfer ribbon

E-Mail: [info@labelident.de](mailto:info@labelident.de)  
Internet: [www.labelident.com](http://www.labelident.com)

The standard-quality wax ribbon can be used with low print temperatures while maintaining good print quality. Contrast-rich print results can be achieved even on rough paper labels. A good transfer rate can be obtained at print speeds of up to 150 mm/s. The ribbons are compatible with all common flathead thermal transfer printers.

#### Material Specifications:

Quality	Wax
Print Head	Flathead
Liner	PET, 4.5µm

#### Print Specifications:

	Value (Tolerance)	Unit
Print Speed	50-150 (+/- 10%)	mm/s
Melting Temperature	70 (+/- 10%)	°C DSC
Optical Density Ribbon	1.2 (+/- 10%)	D
Optical Density Print Result	1.25-2 (+/- 10%)	D
Total Ribbon Thickness	7 (+/- 10%)	µm

#### Resistance:

	Vellum	PE	PP	
Scratch Test <sup>2</sup>	8	13	12	cycles
Smear Test <sup>3</sup>	>1000	>1000	>1000	cycles
Ethanol <sup>3</sup>	30	12	15	cycles
Petrol <sup>3</sup>	1	1	1	cycles
Water <sup>3</sup>	substrate destroyed	>1000	>1000	cycles

\*Test methods: Manufacturer's Test method, except: 2= Taber 250g, 3=Crockmeter 355g

**Certifications:** Material is REACH compliant and ISEGA certified.

**Printability:** Suited best for uncoated paper materials.

**Storage:** Material is stable for one year stored at max. 10-35°C and 30-80% rel. humidity. Direct sunlight and putting pressure on the ribbons should be avoided by all means.

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: August 2018.